

Product Description:


Mylar® 813 is a biaxially oriented clear polyester film, treated on one surface to give excellent adhesion to various inks and coatings.

Typical ink systems used are vinyl and nitro-cellulose, although printing trials are recommended to confirm ink suitability.

Mylar® 813 is widely used in applications where high quality printing is required.

Key Features:

- Superb printability with a wide range of inks
- Good clarity allows inks to shine through when reverse printed
- Excellent thermal and dimensional stability



Storage

Recommended storage conditions: 10°C – 25°C; 20% – 50% RH
Shelf Life: 12 months from delivery date (under recommended storage conditions)

TYPICAL VALUES		MD = Machine Direction, TD = Transverse Direction			
Property	Test method	Unit	Direction	Typical values	
Film thickness	-	micron		12	23
Film yield	-	m ² /Kg		59.9	31.1
Unit weight	-	g/m ²		17	32
Density	ASTM D1505	g/cc		1.4	
Haze	ASTM D1003	%		4.5	7.5
Total light transmittance (max)	ASTM D1003-77 (Gardner hazemeter)	%		87.9	87.7
Tensile strength at break (minimum)	ASTM D882-80	Kgf/mm ²	MD	20	
			TD	26	
Elongation at break	ASTM D882-80	%	MD	125	
			TD	80	
Coefficient of static friction (slip)	ASTM D1894-78	-		0.4	
Upper melt temperature	ASTM E794-85	°C		255 to 260	
Coefficient of thermal expansion (between 20 and 50°C)	-	cm/cm/°C	MD	19 x 10 ⁻⁶	
			TD	16 x 10 ⁻⁶	

Mylar® 813 complies with the following European regulations and directives: EU10/2011 and its amendment 1282/2011 relating to materials and articles intended to come into contact with food



HiFi Polyester Film Is Your Trusted Expert In Polyester Film Solutions

- Expert advice.
- Premium PET films.
- Europe's leading converter & distributor.



Wide range of PET Films



Custom Converting
Reels & Sheets



Short Lead Times

Specialist Facility for Advanced Polyester Film Conversion and Heat Stabilisation



✓ Polyester film slitting



✓ Clean room conversion




✓ Polyester film wholesale



✓ Polyester film sheeting



✓ Thermal polyester stabilisation



✓ Custom converting

Expert Technical Support to Help You Find the Right Polyester (PET) Film Solution

Our in-house specialists provide guidance on material selection, ensuring you get the best polyester film for your specific application and performance requirements.

Contact us for expert help



HiFi Polyester Film UK

UK & Rest of World

Stevenage, United Kingdom
+44 (0) 1438 314 354
sales@hififilm.com



HiFi Polyester Film Netherland

Northern Europe

Zwaag Netherlands
+31 (0) 229 272 282
nlsales@hififilm.com



HiFi Polyester Film France

Southern Europe

BRUSSIEU, France
+33 (0) 437 226 098
lyonsales@hififilm.com



HiFi Polyester Film Ireland

Ireland

Ranelagh, Dublin
+353 (0) 87 257 3698
ray.faughnann@hififilm.com



www.hifipolyesterfilm.com

